


# Cetol WV 880 BPD



## Product description

Waterborne impregnation (liquid wood preservative) to protect against blueness and rot, external  
- deep penetration  
- good run-off properties  
- low-odour

## Active ingredient

0,3 g/100 g Propinylbutylcarbamat iodine 0,9 g/100 g Propiconazol  
Wood protection agents must be registered according to the BPD. (BPD = Biocide Product Directive)  
Approval number: DE-2013-MA-08-00005  
The active substances are notified acc. to guideline 98/8/EG and correspond to the specification EN 599 against blue stain and rot fungi.

## Uptake consumption

The examination follows the uptake value: 120-160 ml/m<sup>2</sup> or 123-164 g/m<sup>2</sup> for timber in the resistance classes 3-5

## Colour

Colourless

## Binder type

Alkyd resin

## Density (specific weight)

approx. 1.00 - 1.03 kg/l

## Packaging

2.5 l, 20 l, 120 l

## Processing

dipping, flow-coating  
Processing viscosity is approx. 11 seconds in a DIN cup 4 mm or approx. 23 - 25 seconds in a ISO cup 3 mm at 20 °C material temperature

## Consumption

90 - 160 ml/m<sup>2</sup>, depending on application method, type and absorption of timber (exact values must be established by tests)

## Thinning

Do not dilute!

## Application temperature

15 - 25 °C for substrate, air and material at approx. 60 % R.H.

## Drying time

|            |                                                |                     |
|------------|------------------------------------------------|---------------------|
| Drying at: | Standard atmosphere: 23 °C / 50% rel. humidity | Forced at 40 °C     |
| Dust dry   | approx. 60 minutes                             | approx. 30 minutes  |
| Sandable   | ---                                            | ---                 |
| Recoatable | approx. 4 - 6 hours                            | approx. 1 - 2 hours |

## Drying

The drying process of the coating depends on the applied film thickness and may be delayed when using timber with a high extractive contents or drying in damp/cold conditions. During the drying process, always ensure for adequate temperature and ventilation. If the drying conditions are not met, damages within the coating cannot be excluded.

## Cleaning of equipment

Clean with water immediately after use and, if required, add some commercially available washing-up liquid or ST 830.

## Storage

The minimum shelf life in the unopened original container is two years; Storage temperature +5 - +30 °C.  
After expiry of the BDD, the product may still be processable, but the product properties may differ from "fresh" material. For that reason, the user must apply expired material with particular attention.  
Started containers must be closed carefully! Store in a cool but frost-free place.  
Dipping tanks containing material must be covered correctly and stirred or circulated regularly.

## Disposal

Only empty containers may be recycled. Dispose of material residues according to local regulations. The EC waste code applicable to such material is: 03 02 02.

## Safety Data Sheet

Further data in the Material Safety Data Sheet according to 91/155/EEC  
[www.sikkens-wood-coatings.com](http://www.sikkens-wood-coatings.com) Downloads Safety Data Sheets

## Warning

The impregnation serves as a protection of none statically subjected wooden constructions without earth contact, exterior, against blue stain and rot according to DIN 68800, part 3.  
Before use, read the identification and product information. Always follow customary protection measures, even when working with low emission products.  
Biocide products must be handled carefully  
Not for use with wood which has got direct contact with foodstuff or animal feedstuff. Only to be used by qualified enterprises.  
Not to be used near waterways. Do not allow the product to enter any water course. Wood preservatives contain biocidal substances for the protection of wood against parasites. They are only to be used according to the instructions and in permitted application areas. Misuse may be harmful to health.  
Dipping tanks or reservoirs: when using metal reservoirs, we recommend using stainless steel, e.g., V2A, the use of other materials may cause corrosion.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2019-04-04

#### VOC Directive

Not subject to marking.

#### General instructions

The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %. The selected wood, the design and the applied layer thicknesses must comply with current technical standards. All horizontal surfaces shall be bevelled by 15 ° and all edges shall be rounded with a radius of at least 2 mm. Joints and open end grains must be sealed to prevent the ingress of water into the structure. The substrates must be dry, free from dust and grease. The selection and application of the coating, especially the colour shade, is important, too. Dark coatings in the exterior may lead to an elevated surface temperature (up to 80 °C).

For use in technical industrial companies. Only to be used in approved and recommended Sikkens Wood Coatings coating systems.

#### Notes

The coating system mentioned here is only an example; other systems are possible. Please refer to the relevant Technical Data Sheets and ask your Sikkens Wood Coatings Sales Representative or the factory for advice about coating systems.

All external materials coming into contact with the coating system (e.g. putty, adhesive tapes, sealants, cleaners, etc.) must be tested for compatibility by the user.

Intermediate sanding may only be done after the subsequent coating.

#### Coating recommendation

All waterborne and solventborne paint systems can be used on the well dried impregnation. If a separate rot impregnation system is not required, separate impregnation is not necessary.

We do not recommend using the product in whitish, translucent colour systems such as "opal white" because it could cause yellow discolouration.

#### Coating system : Stable wooden constructions

|              |                                                                                                                             |
|--------------|-----------------------------------------------------------------------------------------------------------------------------|
| Impregnation | Cetol WV 880 BPD                                                                                                            |
| Primer       | Cetol WP 566<br>Rubbol WP 194                                                                                               |
| Mid coat     | Cetol WM 610 / WM 665<br>Cetol WM 675                                                                                       |
| Top coat     | Cetol WF 952 / WF 957<br>Cetol WF 945 / WF 960 / WF 965<br>Cetol WF 980<br>Rubbol WF 378 / WF 380<br>Rubbol WF 382 / WF 387 |

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites.

Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue:2019-04-04

EMEA HQ

Akzo Nobel Hilden GmbH ● Düsseldorf Str. 96 - 100 ● 40721 Hilden ● Deutschland ● [www.akzonobel.com/wood](http://www.akzonobel.com/wood)

**AkzoNobel**