



ELASTOFILL[®]

Elastic jointing paste based on acrylic dispersions

- Forms a rubberlike mass with permanently high elasticity (> 900%) after evaporation of the water
- Can absorb strong expansions and deformations
- Alkali resistant
- Very resistant to ageing
- Waterproof

ELASTOFILL®

DESCRIPTION

An elastic, paintable jointing paste based on acrylic dispersions for sealing, jointing, filling.

RECOMMENDED USE

Sealing, jointing, filling, fixing, glueing on concrete, wood, metal, glass, hard PVC, tiles, plaster, alu-bitumen, etc.

TECHNICAL DATA

Density: ± 1,3

DRYING TIMES AT 20°C/RH 50%

Touch dry: 3 hours, film thickness 8 mm
Dry to handle: 8 hours, film thickness 8 mm
Dry to recoat: 1 day, film thickness 8 mm
Fully cured: ± 1 week, film thickness 8 mm

For a joint of 10 mm wide and 15 mm deep: ± 6 meters run.
Jointing paste has to be applied in maximum 10 mm wet film thickness.

SURFACE PREPARATION

Grind out fine cracks in V-shape till about 0,5 cm wide; if depth > 1/2 x width, apply a back filling. The crack edges must be primed with Parafix, Pegafix or Vernac (diluted with Thinner 22). Hard PVC is to be primed with Primer 44 HS, metal and glass with diluted Noxyde.

DIRECTIONS FOR USE

Manual spray gun (nozzle free to choose) - spatula, palette knife, glue spreader (combed lime rills ± 3 mm thick).

APPLICATION CONDITIONS

> 5°C, Max. R.H. 80%

Water. After drying Elastofill can only be removed mechanically or softened with a synthetic thinner; then remove by rubbing or scratching.

REMARKS

Joints have to be smoothened with a finger or with a cloth soaked in Thinner 22 or in water (+ soap).

The surface in contact with the air must be sufficiently large, since Elastofill is to be transformed into a rubber like mass by evaporation of the water.

On porous surfaces, always use an appropriate primer.

Elastofill can be recoated with the following paints: acrylic paints Murfill, Paracem (Elastofill has to be isolated first with Porisol), Paracem Semi-Gloss, Pegacryl, Pegacryl Satin for inside and outside works, Pegaflor for inside works; with high and satin gloss alkyd enamels; with Porisol and Pegatex.

SAFETY DATA

VOC limit: 5 g/l
Flashpoint: Not flammable
Remarks regarding safety: Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Date issued: 07/03/2019

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zolem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu