



MUR-FILLER

Elastic joint filler

- Elastic
- High filling power
- Not sandable (contains quartz)

MUR-FILLER

DESCRIPTION

Elastic joint filler for reparation of active and non-active cracks, can be used interior and exterior.

RECOMMENDED USE

- Repair of joints and cracks on inside and outside walls, for instance: stopping up of active and non-active cracks and joints in masonry, concrete and cement fillings.
- Filling up of joints between masonry and windows or door frames.
- Rejointing of paving tiles on terraces provided there is no stagnating water

TECHNICAL DATA

Density: 1,48
Solids content in volume: 69 %
Solids Content in weight: 79 %

DRYING TIMES AT 20°C/RH 50%

Touch dry: 16 hours (8 mm wet film thickness)
Dry to handle: 18 hours (8 mm wet film thickness)
Dry to recoat: Minimum 1 day
Fully cured: 1 week

RECOMMENDED WET FILM THICKNESS

10 mm (cons.: 15 kg/m²)

RECOMMENDED DRY FILM THICKNESS

6,9 mm (cons.: 15 kg/m²)
- 50 - 60 cm joint length per tube.
- 1 cm joint depth for a joint in V-shape.

SURFACE PREPARATION

The cracks to be treated must be opened V-shaped, dusted off and impregnated with Primer 44 HS, with Vernac (diluted with 10% Thinner 22) or with Pegafix.

APPLICATION CONDITIONS

Apply in drying conditions at minimum 5°C.
Cleanup with water.

REMARKS

- Contains quartz, so not appropriated as putty
- Manual spray gun: adapt opening of cartridge to the desired joint width

SAFETY DATA

VOC level: mAX; 5g/l
Remarks regarding safety: Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

2 years from date of production in unopened cartridges, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C

Date issued: 10/01/2019

Available colours & pack sizes:Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zolem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu