



## PARACEM® DECO SATIN

### High-quality satin gloss interior wall paint

- Excellent flow
- Good mechanical resistance against rubbing
- Smooth satin aspect
- Closed coating structure
- Washable

# PARACEM® DECO SATIN

## DESCRIPTION

High-quality satin gloss interior wall paint

## RECOMMENDED USE

Decorative and satin finishing for indoor walls and ceilings.

Applicable on most substrates (plaster, bricks, concrete, glass fibre etc.) in residential and public buildings.

## TECHNICAL DATA

Density:	1,32 - 1,36 (white - wit - blanc)
Gloss Level:	Satin
Gloss level at 60°:	Satin Gloss: 25-30%
Gloss level at 85°:	Satin Gloss: 45-50%
Solids content in volume:	42 - 44% (white - wit - blanc)
Solids Content in weight:	57 - 59% (white - wit - blanc)

## DRYING TIMES AT 20°C/RH 50%

Touch dry:	1 hour
Dry to recoat:	2 hours
Fully cured:	2 days

## RECOMMENDED WET FILM THICKNESS

140 µm

## RECOMMENDED DRY FILM THICKNESS

60 µm

## THEORETICAL CONSUMPTION

6 - 10 m²/l

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

Old cleaned layers in good condition and light porous substrates may be recoated directly with Paracem Deco Satin.

Very porous substrates, smooth plaster and water-resistant plasterboard are to be impregnated first with Pegafix.

Nicotine stains must be isolated first with Pegaprim Isofix, Pegamat Aqua or Pegamat RL.

Old damp spots must be isolated with Pegamat RL or Pegaprim Isofix.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim or Pegaprim Xpress).

Metal objects without rust spots are to be pre-treated with Pegalink, Pegaprim Xpress or Galvaprim.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

> 5°C, < 80% R.H.

## APPLICATION & THINNING: BRUSH

Apply undiluted.

## APPLICATION & THINNING: ROLLER

Apply undiluted.

## APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 013 - 019 / Pressure: 160 - 200 bars.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

If required dilute with water.

## CLEANING OF EQUIPMENT / SPILLS

Water.

## REMARKS

In case of application on patterned vinyl wallpaper, Pegaprim Isofix should be used to block plasticizers migration and limit tacking effect.

## SAFETY DATA

VOC level:	30 g/l
VOC readymix:	30 g/l
VOC category:	A/b
VOC limit:	100 g/l
Flashpoint:	Not flammable
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 13/02/2019

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)