



PARASIL COMPACT

High build intermediate coat, siloxane resins

- Waterborne acrylic and polysiloxane resin
- Very thick coat with high covering power
- Application in 1 or 2 coats
- Direct application on well adhering, solid, even and uneven substrates
- Masks haircracking

PARASIL COMPACT

DESCRIPTION

High build priming and intermediate coat based on waterborne acrylic and polysiloxane resins. To be used in combination with ParaSil®.

RECOMMENDED USE

High build priming and intermediate coat for the protection and decoration of new or old exterior walls. Walls in masonry, concrete, hydraulic plasters. Masks hair-line cracking. Maintenance of old elastic paint coats and outer wall insulation.

RECOMMENDED SYSTEM

On bare substrates or old well adhering and compatible undercoats: 1 coat of Parasil

Compact: 500 to 700 g/m² plus 1 or 2 top coats of Parasil.

On very porous substrates: pretreatment with Primer 44 HS – 10 m²/l. Irregular surfaces: levelling with Pegacrete or with a suitable filler.

TECHNICAL DATA

Density:	1,54
Gloss Level:	Matt
Solids content in volume:	49 - 51 %
Solids Content in weight:	67 - 69 %

DRYING TIMES AT 20°C/RH 50%

Touch dry:	4 hours
Dry to recoat:	24 hours

SURFACE PREPARATION

The substrate must be completely clean, dry and solid. In case of contamination by microorganisms the substrate must first be cleaned with a fungicide solution.

DIRECTIONS FOR USE

To ensure homogeneity coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

The works must be performed in conformity with DTU 59-1. Minimum temperature 7°C, maximum 30 °C and maximum relative humidity 80%.

No condensation during drying time. Low temperatures and/or high relative humidity will extend the drying time. Do not apply on hot walls and in direct sunlight.

APPLICATION & THINNING: BRUSH

Synthetic brushes for water dilutable paints

APPLICATION & THINNING: ROLLER

Polyamide rollers with 20 mm long hair or longer according to roughness.

CLEANING OF EQUIPMENT / SPILLS

Water.

SAFETY DATA

VOC level:	35 g/l
VOC ready mix:	35 g/l
VOC category:	A/c
VOC limit:	40 g/l
Flashpoint:	Not flammable
Remarks regarding safety:	Consult safety data sheet and Safety information printed on the can.

SHELF LIFE

1 year from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 7° and 30°C.

Date issued: 27/03/2019

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zolem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu