



### Product Number: 52

### Intumescent Metal Fire Box and Flexible Fire Bag

The product is available as a rigid metal box with a hinged lid and flush lock as standard but a hinged front door is available as an optional extra. The product is also available as a flexible glass-cloth bag with intumescent properties for use where doors open tightly onto walls, allowing full door opening.

This product comprises of the following materials and therefore is supported by the following Health & Safety Data Sheets:

- Zintec (N/A)
- Appendix 1 (Intumescent Material)
- Appendix 3 (Glass Cloth)

\*The information contained in this safety data sheet is given in good faith. It is accurate to the best of our knowledge and belief and represents the most up to date information. The information given in this data sheet does not constitute or replace the user's own assessment of workplace risk as required by other health and safety legislation.

**ENVIROGRAF®****HEALTH & SAFETY DATA SHEET****Appendix 1**

MULTIGRAF INTUMESCENT MATERIAL

---

**1. IDENTIFICATION OF THE PREPARATION AND COMPANY**

---

PRODUCT NAME: Multigraf Intumescent Material  
MANUFACTURER/SUPPLIER: Envirograf  
ADDRESS: Envirograf House, Barrestone, Nr. Dover, Kent, CT15 7JG  
TELEPHONE/FAX: 01304 842555 01304 842666  
EMERGENCY PHONE NUMBER: 01304 842555

---

**2. COMPOSITION/INFORMATION ON INGREDIENTS**

---

## CHEMICAL CONSTITUTION

Mineral Wool Fibre	20-70	%	by	weight
Exfoliating Graphite	20-60	%	by	weight
Organic binder (including adhesive coating)	5.0-30	%	by	weight

---

**3. HAZARDS IDENTIFICATION**

---

Cutting through the material and surface scuffing may release small amounts of airborne fibre, clay and carbon dust which are mechanically irritant to skin, eyes and upper respiratory system.

Based on animal studies, excessive exposure to man made mineral fibre dust may cause lung damage (fibrosis) and tumours.

As with any dust, pre-existing upper respiratory symptoms and lung diseases may be aggravated.

---

**4. FIRST AID MEASURES**

---

SKIN: Rinse affected areas with water and wash gently with soap. Do not use detergent.

EYES: Flush eyes with large quantities of water, Have eye bath readily available in areas where eye contact may occur. Seek medical attention if irritation continues.

INGESTION: Drink plenty of water. Seek medical advice.

INHALATION: Remove to fresh air, drink water and clear throat and blow nose to evacuate fibre/dust. Seek medical attention.

---

## 5. FIRE FIGHTING MEASURES

---

SUITABLE EXTINGUISHING MEDIA: Use extinguishing agent suitable for type of surrounding combustible materials. Do not inhale products of combustion.

---

## 6. ACCIDENTAL RELEASE MEASURES

---

Store product in original wrapping until required for use.  
Do not allow dust to be wind blown. Do not use compressed air to blow dust or fibres.  
Unwanted product should be collected and stored in sealed bags. Dust/fibre should be removed using a suitable vacuum cleaner with HEPA exhaust air filtration and disposal collection bags; used bags to be sealed before disposal. If sweeping is required the area should be damped down with water before brushing

---

## 7. HANDLING AND STORAGE

---

HANDLING: Keep dust generation to a minimum.  
STORAGE: Store dry and cool. Keep in original wrapping until required for use.

---

## 8. EXPOSURE CONTROLS / PERSONAL PROTECTION

---

### APPLICABLE OCCUPATIONAL EXPOSURE LIMITS:

MAN MADE MINERAL FIBRE: \*ME 2.0 fibres/ml & 5 mg/m; (8 hr TWA)  
FINE CARBON DUST: \*OES 3.5 mg/m; (8 hr TWA) and 7 mg/m; (STEL)  
\*(UK Health & Safety Executive - OEL EH40/98)

RESPIRATORY PROTECTION: Wear disposable dust respirator (eg. 3M 8810 or equivalent).  
HAND PROTECTION: Use of gloves is recommended.  
EYE PROTECTION: Wear goggles or safety glasses with side shields. Do not wear contact lenses.  
SKIN PROTECTION: Wear overalls that are loose fitting at the neck and wrists.

---

## 9. PHYSICAL AND CHEMICAL PROPERTIES

---

APPEARANCE: Flexible Grey fibrous mat with black speckle  
DENSITY: 200 - 500 kg/m;  
EXPANSION: Rapid volumetric expansion occurs when product is heated above 100°C  
FLAMMABILITY: Material will sustain combustion for a short period until organic binder (and SAB coating) is burnt out or resulting expansion self-extinguishes.

---

## 10. STABILITY AND REACTIVITY

---

STABILITY / CONDITIONS TO AVOID: Stable.  
MATERIALS TO AVOID: Strong oxidizing agents, strong alkalis and hydrofluoric acid.  
HAZARDOUS DECOMPOSITION PRODUCTS: Combustion products are HRO, CO, COR and hydrocarbons.

---

---

**11. TOXICOLOGICAL INFORMATION**

---

The International Agency for Research on Cancer (IARC) has classified Mineral Wool Fibre as possibly carcinogenic (Group 2B).

---

**12. ECOLOGICAL INFORMATION**

---

This product will remain stable over time with the inorganic components remaining inert.

---

**13. DISPOSAL CONSIDERATIONS**

---

Waste is not classified as a hazardous waste and may be disposed of at a normal licensed industrial waste site. Local regulations should be considered. Waste should be bagged or suitably contained for disposal to prevent any dusts being wind blown during disposal.

---

**14. TRANSPORT INFORMATION**

---

Not regulated for Transport. Ensure that dust is not wind blown during transportation.

---

**15. REGULATORY INFORMATION**

---

LABELLING		
DANGER CLASSIFICATION	-	
CONTAINS:		-
R PHRASES:		-
S PHRASES:		-
NATIONAL REGULATIONS:	-	

---

**16. OTHER INFORMATION**

---

Further information regarding working with man made mineral fibres and measurement techniques may be obtained by referring to Guidance Note EH46 1990 and NDHS59 1998 published by the UK, Health & Safety Executive.

---

\*The information contained in this safety data sheet is given in good faith. It is accurate to the best of our knowledge and belief and represents the most up to date information. The information given in this data sheet does not constitute or replace the user's own assessment of workplace risk as required by other health and safety legislation.



# **ENVIROGRAF®**

## **Appendix 3** **Woven Glass Fabric**

### **DATA SHEET**

Description	Woven glass fabric Starch weave locked
Ends/cm	18.9
Picks/cm	11.1
Weave	4 end satin
Thickness	0.40 mm
Wt/m <sup>2</sup>	430 g/m <sup>2</sup>
Warp count	1360 d'tex
Weft count	1360 d'tex
Fibre type	Cont. fil glass
Filament diameter	9μ
Warp tensile strength	960 N/cm
Weft tensile strength	720 N/cm
Finish	Starch weave lock

Note : All figures quoted are nominal values