



VALTTI INTERIOR WOOD STAIN

wood protection

VALTTI PIRTTI

(formerly Valtti Interior Wood Stain)

DESCRIPTION

Waterborne translucent, quick drying, low odour, decorative wood stain for interior softwoods and hardwoods, available in many attractive colours. Valtti Interior Wood Stain is easily applied by sponge, brush or spray, and when used in conjunction with Valtti Interior Wood Lacquer, gloss or satin, provides the ideal system to protect and enhance the natural beauty of all types of interior wood surfaces.

EXAMPLES OF USE

Interior wood panelling, wall and ceiling cladding, doors, furniture, shelving, cabinets, hand rails, skirtings, architraves, exposed structural timbers, etc.

PROPERTIES

Material Type

Waterborne, acrylate latex interior wood stain.

Coverage

Smooth wood 10 - 16 m²/litre per coat.

Note: The above should only be used as a guide as actual spreading rates will depend upon many factors including timber species, moisture content, absorption, etc.

Solids Volume

4 %

SPECIFICATIONS

Preparation

Remove grease, dirt, wax etc from new wood. Ensure wood surface is dry. Any paint or varnish must be completely removed to bare wood. The wood surface should be well sanded working in the direction of the grain. Dust off. Fill cracks, joints, nails holes etc. with a good quality wood filler.

APPLICATION

Methods

Sponge, brush or spray. Airless spray - use a 0.009 inch (0.23mm) spray tip.

Thinning

Valtti Interior Wood Stain normally requires no thinning. Stir well before and during use.

VALTTI INTERIOR WOOD STAIN

wood protection

Treatment

Apply one coat evenly avoiding overlaps and finishing in the direction of the grain. If a deeper colour is required apply a second coat of Valtti Interior Wood Stain after the first coat has dried. The final depth of colour depends on the porosity of the wood and the amount of stain applied. It is recommended that a test area be applied before carrying out the work. If a lighter shade is required thin Valtti Interior Wood Stain with up to an equal amount of water.

Note: On some dense timbers e.g. Beech, Valtti Color may be preferable due to its greater penetration. The air temperature must be at least 5 °C (41 °F) and the relative humidity less than 80% at the time of application and drying

Protect the material from frost.

Drying times

Normally touch dry after 1 - 2 hours and recoatable after 4 - 6 hours.

Cleaning of equipment

Brushes and tools must be cleaned with water immediately after use.

MAINTENANCE

To ensure low maintenance, finish with Valtti Interior Wood Lacquer (See Valtti Interior Wood Lacquer data sheet).
On floors and other "hard wear" areas Valtti Interior Wood Stain may be overcoated with Valtti Parquet-Ace Lacquer. Valtti Interior Wood Stain may be overcoated with other varnishes and lacquers. We recommend that tests are made to confirm compatability before the work is carried out.

COLOUR RANGE

Available in many attractive colours (See Valtti Color colour card).

PACKAGING

Minimum contents prior to tinting: 0.9 litre, 2.7 litre and 9 litre.



Holman Specialist Paints Ltd.

1 CENTRAL TRADING ESTATE, SIGNAL WAY, SWINDON SN3 1PD
TEL. (01793) 511537 FAX (01793) 431142

The above information is given based on our long experience in the field and research and development work with these types of materials. However, we can only guarantee the consistent quality of our products, the ultimate result depending on factors beyond our control.

For further information or advice contact: Valtti Specialist Coatings Ltd., telephone (0131) 334 4999