

Excellent adhesion to substrates

PRODUCT ADVANTAGES

- For all stages of plasterboard jointing & finishing
- Easy to apply
- Easy to sand
- White
- + Fine finish

INTERIOR READY MIXED JOINT FILLER

GENERAL INFORMATION

Description

Ready mixed joint filler

Intended use

Interior

- Taping and jointing plasterboards
- Fixing corner tapes & beads
- Finishing substrates

Use







Manual application



USE

DILUTION Ready mixed

APPLICATION

- Conditions Do not apply at temperatures of below +8°C or

above +35°C, or at a relative humidity of above

70% H.R.

- Equipment Filling knife, blade, trowel.

- Equipment cleaning With water before completely dry.

Do not throw away into drains, dispose of this material and its container to an approved disposal contractor or taken to municipal collection point. Do not dispose into the

environment.

APPLICATION THICKNESS 3 mm

AVERAGE CONSUMPTION 0.45 kg/lm

SUBSTRATES Plasterboard, old painted substrates.

Substrates must be hard, cohesive, clean, sound and dry according to the local standards.

OVERCOAT Primer, interior conventional paint, light-weight

wall coverings.





INTERIOR READY MIXED JOINT FILLER

TECHNICAL DATA

COMPONANTS Polymer base aqueous phase coat mix, mineral fillers,

additives.

DENSITY 1.7 ± 0.1

pH 8 ± 1

COLOUR White

WORKING TIME AT 20°C Unlimited

WAITING TIME BEFORE OVERCOATING Once completely dry

CLASSIFICATION NF T 36-005 - Famille III, class 2

NORM NF EN 16566

NF EN 13963 - class 3A

V.O.C < 1 g/l (Ready mixed)

HEALTH AND SAFETY

Use in a well-ventilated place. Avoid direct contact

with skin and eyes. Do not breathe dust.

In case of prolonged contact, it is recommended to

wear suitable gloves.

Safety data sheet available on www.beissier.eu or

www.quickfds.com

PACKAGING 7 kg bucket

STORAGE 12 months from date of manufacture, in unopened

original packaging, protected from frost, heat (max. +30°C), sun and moisture. Close well after use. Store

in original packaging.

This data sheet supersedes and replaces any prior sheet relating to the same product.

Date of issue : April 2017

The purpose of this data sheet is to inform our customers about our product's properties. The information presented in the sheet is based on the current state of our knowledge. However, this information is no substitute for a description pertaining specifically to the type and condition of the substrate concerned. Since technical progress is continuously being made, it is our customer's responsibility, prior to use, to check with us that updated edition of this sheet has not been issued.



Beissier - UK · 4th Floor · 300 High Holborn · London WC1 7JH · Fax : 020 7092 669

Customer Service: 020 7092 6696 · contact@beissier.eu