



PARACEM® DECO MATT

High-quality matt interior wall paint

- Excellent flow
- Good mechanical resistance against rubbing
- Smooth mat aspect
- High covering power
- Tendency not to overlap



PARACEM® DECO MATT

DESCRIPTION

Decorative and matt finishing for indoor walls and ceilings. Applicable on most substrates (plaster, bricks, concrete, etc.) as well in private as in public buildings.

RECOMMENDED USE

Decorative and matt finishing for indoor walls and ceilings. Applicable on most substrates (plaster, bricks, concrete, etc.) as well in private as in public buildings.

TECHNICAL DATA

Density:	1,38 - 1,4 (white)
Gloss Level:	Matt
Gloss level at 60°:	Matt: 2-3%
Gloss level at 85°:	Matt: 2-3%
Solids content in volume:	33 - 35% (white)
Solids Content in weight:	50,5 - 52,5% (white)

DRYING TIMES AT 20°C/RH 50%

Touch dry:	30 minutes
Dry to recoat:	1 hour
Fully cured:	2 days

RECOMMENDED WET FILM THICKNESS

140 µm

RECOMMENDED DRY FILM THICKNESS

50 µm

THEORETICAL CONSUMPTION

7 - 10 m²/l per coat

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application

SURFACE PREPARATION

Old cleaned layers in good condition and light porous substrates may be recoated directly with Paracem Deco.

Very porous substrates, smooth plaster and water-resistant platerboard are to be impregnated first with a coat of the 1/1 mixture Pegafix + Paracem Deco with a consumption of 12 m²/l per coat.

Nicotine stains must be isolated first with Pegaprim Isofix, Pegamat Aqua of Pegamat RL.

Old damp spots must be isolated with Pegamat RL or Pegaprim Isofix.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim or Pegaprim Xpress).

Metal objects without rust spots are to be pre-treated with Pegalink, Pegaprim Xpress or Galvaprim.

On glass fibre, apply preferably first a coat of Paracem Deco Soft or Paracem Deco Satin before finishing with a coat of Paracem Deco.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING: BRUSH

Apply undiluted.

APPLICATION & THINNING: ROLLER

Apply undiluted.

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 013 - 019 / Pressure: 160 - 200 bars

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Possible. If necessary dilute with water.

APPLICATION & THINNING: AEROSOL

> 5°C, < 80% R.H.

SAFETY DATA

VOC level:	30 g/l
VOC readymix:	30 g/l
VOC category:	A/a
VOC limit:	30 g/l
Flashpoint:	Not flammable

SHELF LIFE

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 04/04/2019

Available colours & pack sizes:Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zolem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu