

Rubbol WP 112 FR



sikkens
WOOD COATINGS

<p>Product description</p> <p>Waterborne white sprayable primer for façade elements made of spruce, exterior. Fire protection properties according to B-s2,d0 EN 13501-1 (SBI test). Durability of behaviour in the event of fire: Approved according to EN 16755. Approved according to SP Fire 105.</p>	<p>Cleaning of equipment</p> <p>Clean with water immediately after use and, if required, add some commercially available washing-up liquid or ST 830.</p>									
<p>Colour</p> <p>creme white</p>	<p>Storage</p> <p>The minimum shelf life in the unopened original container is two years; Storage temperature +5 - +30 ° C. After expiry of the BBD, the product may still be processable, but the product properties may differ from "fresh" material. For that reason, the user must apply expired material with particular attention. Started containers must be closed carefully! Store in a cool but frost-free place.</p>									
<p>Binder type</p> <p>Acrylate</p>	<p>Disposal</p> <p>Only empty containers may be recycled. Dispose of material residues according to local regulations. The EC waste code applicable to such material is: 08 01 12</p>									
<p>Pigments</p> <p>Titanium dioxide</p>	<p>Safety Data Sheet</p> <p>Further data in the Material Safety Data Sheet according to 91/155/EEC www.sikkens-wood-coatings.com/Downloads/SafetyDataSheets</p>									
<p>Density (specific weight)</p> <p>Approx. 1.37 kg/l</p>	<p>Warning</p> <p>Before use, read the identification and product information. Always follow customary protection measures, even when working with low emission products.</p>									
<p>Packaging</p> <p>20 l</p>	<p>VOC Directive</p> <p>EC limit value for this product (cat. A/d): 150 g/l (2007) / 130 g/l (2010). This product contains max. 50 g/l VOC.</p>									
<p>Processing</p> <p>Spraying Wet layer thickness according to certification.</p>	<p>General instructions</p> <p>The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %. The selected wood, the design and the applied layer thicknesses must comply with current technical standards. All horizontal surfaces shall be bevelled by 15 ° and all edges shall be rounded with a radius of at least 2 mm. Joints and open end grains must be sealed to prevent the ingress of water into the structure. The substrates must be dry, free from dust and grease. The selection and application of the coating, especially the colour shade, is important, too. Dark coatings in the exterior may lead to an elevated surface temperature (up to 80 °C). Prior to reworking, the coating should not be sanded.</p>									
<p>Consumption</p> <p>At least 250 g/m². When diluted with water, the amount applied must be increased accordingly.</p>	<p>For use in technical industrial companies. Only to be used in approved and recommended Sikkens Wood Coatings coating systems.</p>									
<p>Thinning</p> <p>Ready to use. If necessary with water max. 5 %.</p>	<p>Notes</p> <p>The coating system mentioned here is only an example; other systems are possible. Please refer to the relevant Technical Data Sheets and ask your Sikkens Wood Coatings Sales Representative or the factory for advice about coating systems. All external materials coming into contact with the coating system (e.g. putty, adhesive tapes, sealants, cleaners, etc.) must be tested for compatibility by the user. Prior to reworking, the coating should not be sanded.</p>									
<p>Application temperature</p> <p>15 - 25 °C for substrate, air and material at approx. 60 % R.H.</p>										
<p>Drying time</p> <table border="1"> <tr> <td>Drying at:</td> <td>Standard atmosphere: 23 °C / 50% rel. humidity</td> <td>Forced at 40 °C</td> </tr> <tr> <td>dust dry</td> <td>approx. 30 minutes</td> <td>approx. 15 minutes</td> </tr> <tr> <td>Recoatable</td> <td>approx. 1 - 2 hours</td> <td>approx. 30 minutes</td> </tr> </table>	Drying at:	Standard atmosphere: 23 °C / 50% rel. humidity	Forced at 40 °C	dust dry	approx. 30 minutes	approx. 15 minutes	Recoatable	approx. 1 - 2 hours	approx. 30 minutes	
Drying at:	Standard atmosphere: 23 °C / 50% rel. humidity	Forced at 40 °C								
dust dry	approx. 30 minutes	approx. 15 minutes								
Recoatable	approx. 1 - 2 hours	approx. 30 minutes								
<p>Drying time</p> <p>The drying process of the coating depends on the applied film thickness and may be delayed when using timber with a high extractive contents or drying in damp/cold conditions. During the drying process, always ensure for adequate temperature and ventilation. If the drying conditions are not met, damages within the coating cannot be excluded.</p>										

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2018-09-03

EMEA HQ
Akzo Nobel Hilden GmbH ● Düsseldorf Str. 96 - 100 ● 40721 Hilden ● Deutschland ● www.akzonobel.com/wood

AkzoNobel

Coating system : Semi-stable wooden constructions	
Impregnation	---
Primer	Rubbol WP 112 FR
Mid coat	---
Top coat	Rubbol WF 396 Rubbol WF 3300-03-20 Rubbol WF 3310-03-xx

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue:2018-09-03

EMEA HQ
Akzo Nobel Hilden GmbH ● Düsseldorf Str. 96 - 100 ● 40721 Hilden ● Deutschland ● www.akzonobel.com/wood