
TYPE	Water borne acrylic based clear lacquer
USE	For all types of wood For furniture, fittings and other carpentry Only for indoor use
SPECIAL PROPERTIES	Very fast drying Very good stacking properties Nice "glow and depth" Low VOC

TECHNICAL DATA

Density	1.02-1.05 kg/l
Solids	Approx. 30-36 % by weight Approx. 29-33 % by volume
Volatile organic compound (VOC)	See Safety Data Sheet
Gloss	5-60 units Gardner 60°
Storage	See label
System	TEKNOCLEAR AQUA 1332-0X is normally applied in two layers of 60-90 g/m ² each

DIRECTIONS FOR USE

Application method	Conventional spraying Airless spraying Airmix spraying												
Drying time	<table><thead><tr><th></th><th>20°C</th><th>20 min / 50°C</th></tr></thead><tbody><tr><td>Handable</td><td>1 h</td><td>After cooling</td></tr><tr><td>Sanding</td><td>2,5 h</td><td>After cooling</td></tr><tr><td>Stacking</td><td>3-4 h</td><td>After cooling</td></tr></tbody></table>		20°C	20 min / 50°C	Handable	1 h	After cooling	Sanding	2,5 h	After cooling	Stacking	3-4 h	After cooling
	20°C	20 min / 50°C											
Handable	1 h	After cooling											
Sanding	2,5 h	After cooling											
Stacking	3-4 h	After cooling											
Thinner	Water												
Cleaning	Water or TEKNOCLEAN 1954-00, 1T021010												

HEALTH AND SAFETY See Safety Data Sheet.