
TYPE	Water borne acrylic and polyurethane based clear lacquer
USE	For all types of wood For furniture, fittings and other carpentry Only for indoor use
SPECIAL PROPERTIES	Very good resistance to abrasion Good chemical resistance Good drying properties

TECHNICAL DATA

Density	1.03-1.05 kg/l
Solids	Approx. 33-36 % by weight Approx. 30-33 % by volume
Volatile organic compound (VOC)	See Safety Data Sheet
Gloss	20-70 units Gardner 60°
Storage	See label
System	TEKNOCLEAR AQUA 1333-0X is normally applied in two layers of 60-90 g/m ² each

DIRECTIONS FOR USE

Application method	Conventional spraying Airless spraying Airmix spraying												
Drying time	<table><thead><tr><th></th><th>20 °C</th><th>20 min / 50 °C</th></tr></thead><tbody><tr><td>Handable</td><td>1 h</td><td>After cooling</td></tr><tr><td>Sanding</td><td>2.5 h</td><td>After cooling</td></tr><tr><td>Stacking</td><td>3-4 h</td><td>After cooling</td></tr></tbody></table>		20 °C	20 min / 50 °C	Handable	1 h	After cooling	Sanding	2.5 h	After cooling	Stacking	3-4 h	After cooling
	20 °C	20 min / 50 °C											
Handable	1 h	After cooling											
Sanding	2.5 h	After cooling											
Stacking	3-4 h	After cooling											
Thinner	Water												
Cleaning	Water or TEKNOCLEAN 1954-00, 1T021010												
HEALTH AND SAFETY	See Safety Data Sheet												

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.
