

TYPE Water borne acrylic and polyurethane based clear lacquer**USE** For all types of wood
For furniture, fittings and other carpentry
Only for indoor use**SPECIAL PROPERTIES** Very good resistance to abrasion
Good chemical resistance
Good drying properties**TECHNICAL DATA****Density** 1.03-1.05 kg/l**Solids** Approx. 33-36 % by weight
Approx. 30-33 % by volume**Volatile organic compound (VOC)** See Safety Data Sheet**Gloss** 20-70 units Gardner 60°**Storage** See label**System** TEKNOCLEAR AQUA 1333-0X is normally applied in two layers of 60-90 g/m² each**DIRECTIONS FOR USE****Application method** Conventional spraying
Airless spraying
Airmix spraying

Drying time	<u>20 °C</u> <u>20 min / 50 °C</u>	
	Handable	1 h
Sanding	2.5 h	After cooling
Stacking	3-4 h	After cooling

Thinner Water**Cleaning** Water or TEKNOCLEAN 1954-00, 1T021010**HEALTH AND SAFETY** See Safety Data Sheet