

TYPE Water borne acrylic and polyurethane based clear lacquer**USE** For all types of wood
For furniture, fittings and other carpentry
Only for indoor use**SPECIAL PROPERTIES** For dipping applications
Good resistance to abrasion
Good filling properties
Fast drying**TECHNICAL DATA****Density** 1.03-1.06 kg/l**Solids** Approx. 38-42 % by weight
Approx. 36-39 % by volume**Volatile organic compound (VOC)** See Safety Data Sheet**Gloss** 5-70 units Gardner 60°**Storage** See label**System** TEKNOCLEAR AQUA 1333-2X is either applied two layers or one layer on a water borne product**DIRECTIONS FOR USE****Application method** Dipping

Drying time	<u>20°C</u> <u>20 min / 50°C</u>	
	Sanding	2-3 h
Stacking	4-5 h	After cooling

Thinner Water**Cleaning** Water or TEKNOCLEAN 1954-00, 1T021010**HEALTH AND SAFETY** See Safety Data Sheet

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.