

TYPE Water borne acrylic and polyurethane based clear lacquer**USE** For all types of wood
For furniture, fittings and other carpentry
Only for indoor use**SPECIAL PROPERTIES** For dipping applications
Very good resistance to abrasion
Good filling properties
Fast drying**TECHNICAL DATA****Density** 1.03-1.06 kg/l**Solids** Approx. 37-40 % by weight
Approx. 35-38 % by volume**Volatile organic compound (VOC)** See Safety Data Sheet**Gloss** 5-70 units Gardner 60°**Storage** See label**System** TEKNOCLEAR AQUA 1333-3X is either applied two layers or one layer on a water borne product**DIRECTIONS FOR USE****Application method** Dipping

Drying time	<u>20 °C</u> <u>20 min / 50 °C</u>	
	Sanding	2-3 h
Stacking	4-5 h	After cooling

Thinner Water**Cleaning** Water or TEKNOCLEAN 1954-00, 1T021010**HEALTH AND SAFETY** See Safety Data Sheet