

TECHNICAL DATA SHEET

1 29.06.2016

TEKNOCLEAR AQUA

Water borne clear lacquer 1335-5X

TYPE Water borne acrylic based clear lacquer

USE For all types of wood

For furniture, fittings and other carpentry

Only for indoor use

SPECIAL PROPERTIES Very fast drying

Very good stacking properties

Nice "glow and depth"

TECHNICAL DATA

Density Approx. 1.02 kg/l

Solids Approx. 31 % by weight

Approx. 29 % by volume

Volatile organic compound

(VOC)

See Safety Data Sheet

Gloss Approx. 5-60 units Gardner 60°

Storage See label

System TEKNOCLEAR AQUA 1335-5X is normally applied in two layers of 60-90 g/m² each

DIRECTIONS FOR USE

Application method Conventional spraying

Airless spraying Airmix spraying

Drying time 20 °C 20 min / 50 °C

Handable 1 h After cooling Sanding 2 h After cooling Stacking 3 h After cooling

Thinner Water

Cleaning Water or TEKNOCLEAN 1954-00, 1T021010

HEALTH AND SAFETY See Safety Data Sheet

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.