

TEKNOCLEAR AQUA 1336-20
TRANSLUCENT WHITE
Water borne clear lacquer**TYPE** Water borne acrylic based clear lacquer**USE** Wood panels of pine and spruce
Only for indoor use**SPECIAL PROPERTIES** Very fast drying
Good stacking properties
Delays discoloration of knots
Prevents yellowing of the wood**TECHNICAL DATA****Density** Approx. 1.15 kg/l**Solids** Approx. 35 % by weight
Approx. 25 % by volume**Volatile organic compound (VOC)** See Safety Data Sheet**Gloss** Matt, approx. 5 units Gardner 60°**Colour** Translucent white**Storage** See label**System** TEKNOCLEAR AQUA 1336-20 can be painted in one or two layers, normally 60-90 g/m² in each layer. For best result the product should be forced dried.**DIRECTIONS FOR USE****Application method** Conventional spraying
Airless spraying
Airmix spraying**Drying time**

	20 °C	20 min / 50 °C
Handable	1 h	After cooling
Sanding	2.5 h	After cooling
Stacking	3-4 h	After cooling

Thinner Water**Cleaning** Water or TEKNOCLEAN 1954-00, 1T021010**HEALTH AND SAFETY** See Safety Data Sheet