

TEKNOCLEAR AQUA 1336-30
TRANSLUCENT WHITE
Water borne clear lacquer**TYPE** Water borne acrylic based clear lacquer**USE** Wood panels of pine and spruce
Only for indoor use**SPECIAL PROPERTIES** Very fast drying
Very good stacking properties
Low VOC**TECHNICAL DATA****Density** Approx. 1.05 kg/l**Solids** Approx. 35 % by weight
Approx. 32 % by volume**Volatile organic compound (VOC)** See Safety Data Sheet**Gloss** Matt, approx. 5 units Gardner 60°**Colour** Translucent white**Storage** See label**System** TEKNOCLEAR AQUA 1336-30 can be painted in one or two layers, normally 60-90 g/m² in each layer. It can also be used in combination with TEKNOCOAT AQUA SEALER 2700-0X for improved resistance against knot discoloration.
For best result the product should be forced dried.**DIRECTIONS FOR USE****Application method** Conventional spraying
Airless spraying
Airmix spraying

Drying time	<u>20 °C</u> <u>20 min. / 50 °C</u>	
	Handable	1 h
Sanding	2 h	After cooling
Stacking	3 h	After cooling

Thinner Water**Cleaning** Water or TEKNOCLEAN 1954-00, 1T021010**HEALTH AND SAFETY** See Safety Data Sheet