

TYPE Water borne acrylic based clear lacquer**USE** For all types of wood
For furniture, fittings and other carpentry
Only for indoor use**SPECIAL PROPERTIES** Very fast drying
Very good stacking properties
Nice "glow and depth"**TECHNICAL DATA****Density** 1.02-1.04 kg/l**Solids** Approx. 32 % by weight
Approx. 30 % by volume**Volatile organic compound (VOC)** See Safety Data Sheet**Gloss** 5-35 units Gardner 60°**Storage** See label**System** TEKNOCLEAR AQUA 1337-0X is normally applied in two layers of 60-90 g/m² each**DIRECTIONS FOR USE****Application method** Conventional spraying
Airless spraying
Airmix spraying
Curtain coating**Drying time**

	20 °C	20 min / 50° C
Handable	1 h	After cooling
Sanding	2.5 h	After cooling
Stacking	3-4 h	After cooling

Thinner Water**Cleaning** Water or TEKNOCLEAN 1954-00, 1T021010**HEALTH AND SAFETY** See Safety Data Sheet