
TYPE	Water borne acrylic based clear lacquer
USE	For all types of wood For furniture, fittings and other carpentry Only for indoor use
SPECIAL PROPERTIES	Very fast drying Very good stacking properties Nice "glow and depth"

TECHNICAL DATA

Density	1.02-1.04 kg/l
Solids	Approx. 32 % by weight Approx. 30 % by volume
Volatile organic compound (VOC)	See Safety Data Sheet
Gloss	5-35 units Gardner 60°
Storage	See label
System	TEKNOCLEAR AQUA 1337-0X is normally applied in two layers of 60-90 g/m ² each

DIRECTIONS FOR USE

Application method	Conventional spraying Airless spraying Airmix spraying Curtain coating												
Drying time	<table><thead><tr><th></th><th>20 °C</th><th>20 min / 50° C</th></tr></thead><tbody><tr><td>Handable</td><td>1 h</td><td>After cooling</td></tr><tr><td>Sanding</td><td>2.5 h</td><td>After cooling</td></tr><tr><td>Stacking</td><td>3-4 h</td><td>After cooling</td></tr></tbody></table>		20 °C	20 min / 50° C	Handable	1 h	After cooling	Sanding	2.5 h	After cooling	Stacking	3-4 h	After cooling
	20 °C	20 min / 50° C											
Handable	1 h	After cooling											
Sanding	2.5 h	After cooling											
Stacking	3-4 h	After cooling											
Thinner	Water												
Cleaning	Water or TEKNOCLEAN 1954-00, 1T021010												

HEALTH AND SAFETY	See Safety Data Sheet
--------------------------	-----------------------

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.
