

---

<b>TYPE</b>	One component clear lacquer.
<b>USE</b>	For all types of wood and fibreboards. Well fitted for line-application. Only for interior use.
<b>SPECIAL PROPERTIES</b>	Fast drying. Very good surface resistance. Good filling properties. No aromatics. Free from formaldehyde.

---

**TECHNICAL DATA**

<b>Gloss (60°)</b>	5-80 units Gardner
<b>Delivery viscosity</b>	50-55 s, DIN-cup 4, 20 °C
<b>Specific density</b>	0.92-0.96 kg/l
<b>Solids, weight</b>	Approx. 26 % Approx. 19 % by volume
<b>Volatile organic compound (VOC)</b>	See Safety Data Sheet.
<b>Storage</b>	Storage: See label.
<b>System</b>	Can be used both as primer and as topcoat. Recommended amount applied 2 x 80-150 g/m <sup>2</sup> .

**DIRECTIONS FOR USE**

<b>Application method</b>	Conventional-, high-pressure- and automatic spraying. Curtain coating.		
<b>Drying</b>		<u>20 °C</u>	<u>50 °C</u>
	Dry for handling	60 min.	30 min.
	Dry for stacking	2 hours	1 hour
<b>Thinner</b>	TEKNOSOLV 1135-93.		
<b>Cleaning</b>	TEKNOSOLV 1135-93.		

<b>HEALTH AND SAFETY</b>	See Safety Data Sheet.
--------------------------	------------------------