

TECHNICAL DATA SHEET

2 22.06.2016

TEKNOCOAT 1689

One component lacquer 1689-3X

TYPE One component lacquer.

USE For all types of wood and fibreboards. Only for interior use.

SPECIAL PROPERTIES Very fast drying. Scratch resistance. No aromatics.

TECHNICAL DATA

Gloss (60°) 5-50 units Gardner

Viscosity 30-35 s, DIN-cup 4, 20 °C

Density 0.90-0.98 kg/l

Solids Approx. 24 % by weight

Approx. 17 % by volume

Volatile organic compound

(VOC)

See Safety Data Sheet.

Storage: See label.

System Can be used both as primer and as top coat.

Recommended amount applied 2 x 80-150 g/m².

DIRECTIONS FOR USE

Application method Conventional, automatic and high-pressure spraying and curtain coating.

Drying <u>20 °C</u> <u>50 °C</u>

Dry for handling 1 hour 30 min.
Dry for stacking 2 hours 1 hour

Thinner TEKNOSOLV 1135-93.

Cleaning TEKNOSOLV 1135-93.

HEALTH AND SAFETY See Safety Data Sheet.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.