

## **TECHNICAL DATA SHEET** 2 02.09.2014

**TEKNOCOAT AQUA 1826** 

One component topcoat 1826-XX

ТҮРЕ	One component air-drying topcoat, water borne.		
USE	For spot repair of previously painted PUR-subjects. For surfaces used indoors.		
SPECIAL PROPERTIES	Quick drying. Provides a robust surface resistant to weak acids, bases, oils and water.		
TECHNICAL DATA			
Finish	Approx. 20-30 / 60°		
Colours	Is only supplied in white (TS 8696)		
Delivery viscosity	Approx. 80 Krebs Unit (KU) at 20 °C.		
Density	Approx. 1.2 kg/l		
Solids, by weight	Approx. 50 %		
Volatile organic compound (VOC)	See Safety Data Sheet.		
Application method	Spraying.		
Drying method	Air, oven drying.		

DIRECTION FOR USE			
Surface preparation	PUR-surfaces:	Alkaline cleaning to remove oil and dirt.	
	Paint repair on painted PUR-surfaces:	Cleaning of freshly painted PUR-subjects should not be necessary. Repair of an item can be sanded lightly with fine sandpaper or use a planner.	
		If there are dark coloured marks it can be an advantage to remove these with a soft spirit cloth before painting so you can do with a very thin layer of paint repair.	
Application conditions	The surface to be painted must be dry. When coating and curing the temperature of the air, paint and surface must be above 15 °C and the relative air humidity below 70 %.		
Application	<u>Equipment</u> Kop spray gun	<u>Thinner</u> Water	
Drying	<u>At 50 % RH</u> Dry for handle Dry for stacking	<u>20 °C</u> Approx. 1 hour Approx. 2 hours	Forced drying at 50 °C - Approx. 30 minutes
Recommended amount to be applied	Approx. 100 µm wet.		
Cleaning of equipment	For cleaning of tools use water or a mixture of TEKNOSOLV 7030 and water.		
HEALTH AND SAFETY	See Safety Data Sheet.		
ADDITIONAL INFORMATION	Storage: See label. Store in a tightly closed container. The product must be stored frost-free and not above 30 °C Is available in 10 litres plastic packing.		

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.