
TYPE	Water borne pigmented top coat for curtain coating
USE	For MDF and wood panels
SPECIAL PROPERTIES	Good levelling and fast drying

TECHNICAL DATA

Density	Approx. 1,17 kg/l
Solids	Approx. 43 % by weight Approx. 32 % by volume
Volatile organic compound (VOC)	See Safety Data Sheet
Storage	See label
Colour	RAL 9003
System	TEKNOCOAT AQUA 2572-21 can be used on water borne primers

DIRECTIONS FOR USE

Application method	Curtain coating
Drying time	Dry for handling <u>20° C</u> <u>50 °C/30 min.</u> 1 h After cooling
Thinner	Water
Cleaning	Water or TEKNOCLEAN 1954-00

HEALTH AND SAFETY See Safety Data Sheet.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.
