
TYPE	Water borne topcoat.
USE	For solid wood, MDF and fibre board. Very suitable for line-application. Only for interior use.
SPECIAL PROPERTIES	Very fast drying. Very good stacking properties. Good levelling. Good filling properties.

TECHNICAL DATA

Density	Approx. 1.03-1.21 kg/l, depending on the amount of pigments Base 1: Approx. 1.21 kg/l Base 2: Approx. 1.09 kg/l Base 3: Approx. 1.03 kg/l
Solids	Approx. 32-45 % by weight, depending on the amount of pigments Approx. 30-35 % by volume, depending on the amount of pigments Base 1: Approx. 47 % by weight, approx. 34 % by volume Base 2: Approx. 37 % by weight, approx. 31 % by volume Base 3: Approx. 32 % by weight, approx. 30 % by volume
Volatile organic compound (VOC)	See Safety Data Sheet.
Storage	See label.
Gloss (60°)	Approx.: 10-50 Gardner 60°
Colours	Available in different colours and tintable with TEKNOCOLOR in gloss 25.
System	TEKNOCOAT AQUA 2575-3X can be used on water borne primers.

DIRECTIONS FOR USE

Application method	Conventional spraying. Airless spraying. Airmix spraying.		
Drying		<u>20 °C</u>	<u>20 min. / 50 °C</u>
	Dry for handling	1 hour	After cooling
	Dry for stacking	2 hours	After cooling
Thinner	Water		
Cleaning	Water or TEKNOCLEAN 1954-00, 1T021010.		

HEALTH AND SAFETY See Safety Data Sheet.