

**TYPE** Water borne acrylic based pigmented topcoat.**USE** For most types of wood.  
For furniture, fittings and other carpentry.  
Only for indoor use.**SPECIAL PROPERTIES** Very good chemical resistance.  
Very good scratch resistance.**TECHNICAL DATA****Density** Approx. 1.20 kg/l**Solids** Approx. 48% by weight  
Approx. 36 % by volume**Volatile organic compound (VOC)** See Safety Data Sheet.**Gloss** 30-60 units Gardner 60°**Storage** See label**System** TEKNOCOAT AQUA 2585-13 is normally applied in one or two layers on water borne primer. Best result when forced dried.**DIRECTIONS FOR USE****Application method** Conventional spraying  
Airless spraying  
Airmix spraying**Drying time**

	20 °C	60 min / 50 °C
Handable	2h	After cooling
Stacking	24h	After cooling + 12h

**Thinner** Water**Cleaning** Water or TEKNOCLEAN 1954-00, 1T021010**HEALTH AND SAFETY** See Safety Data Sheet