

TECHNICAL DATA SHEET

1 1.11.2017

TEKNOCOAT AQUA PRIMER 1866-07

Water borne primer

TYPE Water borne pigmented primer with good surface properties

USE For wood panels and fibreboards

Suitable for vertical application Suitable for line application

Only for indoor use

SPECIAL PROPERTIES Low effect on grain raising

Good filling properties

Good levelling

Good sanding properties

Fast drying

TECHNICAL DATA

Density Approx.1.40 kg/l

Solids Approx. 60 % by weight

Approx. 43 % by volume

Volatile organic compound

(VOC)

See Safety Data Sheet

Storage See label

Colour White

System TEKNOCOAT AQUA PRIMER 1866-07 is normally applied in two layers. Best result

when force dried. Overcoating with water borne topcoats.

DIRECTIONS FOR USE

Application method Conventional spraying

Airless spraying Airmix spraying

Drying time 20 °C 20 min. / 50 °C

Handable 1 h After cooling Sanding 2 h After cooling

Thinner Water

Cleaning Water or TEKNOCLEAN 1954-00, 1T021010

HEALTH AND SAFETY See Safety Data Sheet

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.