

TYPE Water borne pigmented primer**USE** For wood panels and fiberboards
Suitable for line application
Only for indoor use**SPECIAL PROPERTIES** Good filling properties
Good levelling
Fast drying
Good sanding properties**TECHNICAL DATA****Density** Approx. 1.37 kg/l**Solids** Approx. 54 % by weight
Approx. 37 % by volume**Volatile organic compound (VOC)** See Safety Data Sheet**Storage** See label**Colour** White**System** TEKNOCOAT AQUA PRIMER 1866 is normally applied in two layers. Best result when force dried. Overcoating with water borne topcoats.**DIRECTIONS FOR USE****Application method** Conventional spraying
Airless spraying
Airmix spraying**Drying time**

	20 °C	20 min / 50 °C
Handable	1 h	After cooling
Sanding	2 h	After cooling

Thinner Water**Cleaning** Water or TEKNOCLEAN 1954-00, 1T021010**HEALTH AND SAFETY** See Safety Data Sheet

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.