

TEKNOCOAT AQUA PRIMER 1867-10
Water borne primer

TYPE	Water borne pigmented primer for blocking discoloration of knots.
USE	For pine wood panels Only for indoor use
SPECIAL PROPERTIES	Low pH, very important with careful cleaning of equipment before and after use.

TECHNICAL DATA

Density	Approx. 1.29 kg/l
Solids	Approx. 51 % by weight Approx. 37 % by volume
Volatile organic compound (VOC)	See Safety Data Sheet.
Storage	See label
System	TEKNOCOAT AQUA PRIMER 1867-10 is normally sprayed in one layer, 90-150 g/m ² . Best resistance against knot discoloration is achieved when applying two thin layers compared to one thick layer. Only flutter or very slight sanding is recommended. Overcoating with water borne topcoats.

DIRECTIONS FOR USE

Application method	Conventional spraying Airless spraying Airmix spraying
Drying time	Dry for handling <u>20 °C</u> <u>50 °C/30 min.</u> 2 h After cooling
Thinner	Water
Cleaning	Water

HEALTH AND SAFETY See Safety Data Sheet.