

DATA SHEET 1291 5 10.01.2012	TEKNOCRYL 1295-05 Acrylic Top Coat			
PAINT TYPE	TEKNOCRYL 1295-05 is a one pack, acrylic top coat with semigloss finish and based on a modified acrylic resin.			
USAGE	It is used as a top coat in TEKNOSAFE 2002-00, HENSOTHERM 3 KS and HENSOTHERM 4 KS - fire resistance paint systems and in acrylic systems for metal surfaces.			
SPECIAL PROPERTIES	The binder of the paint is an acrylic resin modified with halogen-free plasticizers. The resistance to solvents is limited. The heat resistance is up to +80 °C.			
TECHNICAL DATA				
Solids	41 ±2% by volume			
Total mass of solids	abt. 650 g/l			
Volatile organic compound (VOC)	abt. 530 g/l			
Recommended film thickness and theoretical spreading rate	Dry film (µm)	Wet film (µm)	Theoretical s	preading rate (m²/l)
	40	97		10,2
			oo thick coats are applied, it is e than double of the thickest r	
Practical spreading rate	The values depend on the application technique, surface conditions, overspray, etc.			
Drying time at +23°C / 50% RH (dry - dust free (ISO 9117-3:2010) - touch dry (DIN 53150:1995)	film 40 μm) after 2 h after 3 h			
Overcoatable, 50% RH (dry film 40	μ <u>m)</u>	·		7
			itself max.	+
	surface temperature	after 8 h	-	-
	+23°C	after 4 h	-	1
	Increase in film thick down the drying proc		humidity of the air in the dryin	⊐ g space usually slow
Thinner, clean up	TEKNOSOLV 1640 or TEKNOSOLV 1639			
Finish	Semigloss			
Colours	The paint is included in the Teknomix tinting system.			
SAFETY MARKINGS	See Material Safety	v Data Sheet.		PTO

РТО

DIRECTION FOR USE Surface preparation	Remove from the surfaces any contaminants that might be detrimental to surface preparation and painting. Remove also water-soluble salts by using appropriate methods.			
	The place and time of the preparation are to be chosen so that the prepared surface will not get dirty or damp before the subsequent treatment.			
	OLD PAINTED SURFACES SUITABLE FOR OVERCOATING: Any impurities that might be detrimental to the application of paint (e.g. grease and salts) are removed. The surfaces must be dry and clean. Old, painted surfaces that have exceeded the maximum overcoating time are to be roughened as well. Damaged parts are prepared in accordance with the requirements of the substrate and the maintenance coating.			
Application conditions	The surface to be painted must be dry. The temperature of the ambient air, the surface and the paint shall be above 0°C and the relative air humidity below 80% during the application and drying period. Additionally the temperature of the surface to be painted and the paint must be at least 3°C above the dew point of the ambient air.			
Application	Before use stir the paint thoroughly.			
	For overcoating on TEKNOSAFE 2002-00, HENSOTHERM 3 KS and HENSOTHERM 4 KS intumescent paints TEKNOCRYL 1295-05 is thinned 20 - 40% by TEKNOSOLV 1640 (slow thinner) or TEKNOSOLV 1639 (fast thinner).			
	Apply by brush or airless spray. Use airless spray nozzle size 0.013 - 0.017".			
ADDITIONAL INFORMATION	The storage stability is shown on the label. Store in a cool place and in tightly closed containers.			
	Additional instructive information for surface preparation can be found in standards EN ISO 12944-4 and ISO 8501-2.			

The information of this data sheet is normative and based on laboratory tests and practical experience. Teknos guarantees that the product quality conforms to our quality system. Teknos accepts, however, no liability for the actual application work, as this is to a great extent dependent on the conditions during handling and application. Teknos accepts no liability for any damage resulting from misapplication of the product. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.