
TYPE	TEKNOCRYL AQUA 98040 is based on a combination of alkyd/acrylic.
USE	Is applied on metal and plastic. For interior and exterior use.
SPECIAL PROPERTIE	-

TECHNICAL DATA

Solids by volume	30-50 %		
Volatile organic compound (VOC)	40 ±10 g/l depending on colour.		
Density	1.0-1.3		
Recommended film thickness and theoretical spreading rate	Dry film (µm) 60	Wet film (µm) 110-200	Theoretical spreading rate (m ² /l) 5-8
Drying time at 20 °C / 40-60 % RH (150 µm wet film)			
- dust free	30 min.		
- surface dry (ISO 1517)	1-2 hours		
- overcoatable	Overcoatable by itself after min. 3 hours and max. 7 days.		
Drying time – stoving or forced drying 40-60 °C	De-aeration time: 10 min. Stoving time: 20 min.		
Thinner	Water.		
Cleaning	Water or TEKNOCLEAN 90900-00 G5798.		
Gloss (60°)	By agreement.		
Colour range	Available in all RAL and NCS-S colours or at your request.		
Storage	See page 2.		
HEALTH AND SAFETY	See Safety Data Sheet.		

DIRECTIONS FOR USE

Surface preparation

The surface must be clean, dry and free from grease, oil, rust and iron scale.

Cold-rolled steel: Degreasing and phosphatising.

Hot-rolled steel: Abrasive blasting to preparation grade SA 2½ (ISO 8501-1:1988).

Galvanized steel: Please contact our technical department for further information.

Other surfaces: Please contact our technical department for further information.

Application conditions

Application to follow right after the surface preparations. When coating the temperature of the ambient air, paint and surface must be above 10 °C and the relative humidity below 60 %. Additionally, the temperature of the surface to be painted must be at least 3 °C above the dew point of the ambient air to avoid condensation.

Application data

<u>Equipment</u>	<u>Nozzle</u>	<u>Delivery viscosity</u>
Airmix	0.011"-0.013"	Will be adjusted to fit the actual conditions
Airless	0.011"-0.013"	
Air-spraying	0.011"-0.013"	

ADDITIONAL INFORMATION

The storage stability is shown on the label.
Store in a tightly closed container.

The product must be stored at temperatures between +5 °C and +25 °C.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.