
TYPE	Two-component polyurethane lacquer.
USE	For all types of wood and fibreboards. Only for interior use.
SPECIAL PROPERTIES	High gloss. Fast drying. Good abrasion resistance. Good surface resistance.

TECHNICAL DATA

Gloss (60°)	90-100 units Gardner
Viscosity	50-60 s, DIN-cup 4.
Density	1.00 kg/l
Solids	36 % by weight 29 % by volume
Volatile organic compound (VOC)	See Safety Data Sheet.
Storage	Storage: See label.
Colour range	Clear and special colours.
Mixing ratio	1:1 BASE:HARDENER TEKNODUR HARDENER 1668-19
Pot life	24 hours
System	Recommended amount applied 2 x 80-120 g/m ² .

DIRECTIONS FOR USE

Application method	Conventional and automatic spraying. Dipping.						
Drying time	<table><tr><td></td><td><u>20 °C</u></td></tr><tr><td>Sanding</td><td>4-6 h</td></tr><tr><td>Stacking</td><td>16-24 h</td></tr></table>		<u>20 °C</u>	Sanding	4-6 h	Stacking	16-24 h
	<u>20 °C</u>						
Sanding	4-6 h						
Stacking	16-24 h						
Thinner	TEKNOSOLV 1135-25.						
Cleaning	TEKNOSOLV 1135-25.						

HEALTH AND SAFETY	See Safety Data Sheet.
--------------------------	------------------------