

**TEKNOL 1888**
transparent primer

PAINT TYPE	A water-borne, fast drying and transparent alkyd/acrylic primer that will bring out the natural surface pattern of wood.
USAGE	For industrial surface treatment of wooden facade boards and prefabricated units for wooden houses. To make sure that the product is suitable for the usage in question the paint manufacturer is to be contacted before the product is taken into use.
SPECIAL PROPERTIES	Protects wood until it is top coated at the building site or in the factory. In any case the top coating should be done as soon as possible, the next summer at the latest.

TECHNICAL DATA

Solids	23 ±2% by volume
Total mass of solids	abt. 270 g/l
Volatile organic compound (VOC)	abt. 3 g/l
Practical spreading rate	abt. 5 - 10 m ² /l
Drying time at +23°C / 50% RH - dry to handle Overcoatable	after about 30 min after about 2 h Increase in film thickness and rise in the relative humidity of the air in the drying space usually slow down the drying process. When using accelerated drying ask for the instructions from the manufacturer.
Thinner, clean up	Can be diluted 0 - 10% with water. Wash the equipment with water.
Colours	Transparent wood stain colours.
SAFETY MARKINGS	See Material Safety Data Sheet.

PTO

NOTE! Because of the danger of self-ignition, any waste from the product, spray mist and soiled rags etc. are to be kept in a fire-proof place in air-tight containers, alternatively the waste is to be burned. Immersion in water is also recommended. (See Material Safety Data Sheet, paragraph 7.1.)

DIRECTION FOR USE**Surface preparation**

The surface must be clean and dry.
The moisture content of the wood is to be below 20%.

Application conditions

The temperature of the air, the surface and the paint shall be above +15°C and the relative humidity of the air below 80% during the time of application and drying.

Application

Before use stir the paint thoroughly.
Apply by vacuum- or brush machine, spray or by brush.

The primer can be applied 1 or 2 times, appr. 100 g/m² /layer.

ADDITIONAL INFORMATION

The storage stability is shown on the label. Store in a tightly closed containers. The best storage temperature is +10°C - +25°C.

MUST NOT FREEZE.

The information of this data sheet is normative and based on laboratory tests and practical experience. Teknos guarantees that the product quality conforms to our quality system. Teknos accepts, however, no liability for the actual application work, as this is to a great extent dependent on the conditions during handling and application. Teknos accepts no liability for any damage resulting from misapplication of the product. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.
