



TEKNOPOX PUTTY 100-11

Epoxy Putty

TYPE	A solvent-free, two-pack epoxy putty.	
USAGE	TEKNOPOX PUTTY 100-11 is used for filling holes and crack in wood, plywood and metal.	
SPECIAL PROPERTIES	Does not shrink or swell. It is easy to apply and to sand. Paints and film coatings have good adhesion to the putty. TEKNOPOX PUTTY 100-11 withstands well heat, weathering and chemicals.	

TECHNICAL DATA		
Mixing ratio	Base (Comp. A):	2 parts by volume or 3 parts by weight
	Hardener (Comp.B): TEKNOPOX PUTTY HARDENER 7241-02	1 part by volume or 1 part by weight
Pot life, +23 °C	1 h	
Solids	100 % by volume	
Total mass of solids	abt. 1200 g/l	
Volatile organic compound (VOC)	abt. 0 g/l	
Drying time at +23°C / 50% RH		
- dust free (ISO 9117-3:2010)	after 4 h	
- touch dry (DIN 53150:1995)	after 8 h	
- fully cured	after 7 days	
Clean up	TEKNOSOLV 9506	
Colours	Birch	
SAFETY MARKINGS	See Material Safety Data Sheet.	

PTO

DIRECTION FOR USE

The surface to be treated must be clean and dry. Take into consideration the pot life of the mixture when estimating the amount to be mixed at a time. Stir with a putty knife till the mixture is homogenous and a uniform colour.

The drying process can be speeded up by heat.

Rub down the filled surface before it is painted.

Application conditions

The temperature of the ambient air, the surface and the putty shall be above +10°C and relative air humidity below 80 % during the application and drying period.

ADDITIONAL INFORMATION

The storage stability is shown on the label. Store in a dry, well ventilated place and in tightly closed containers separate from foodstuff. The best storage temperature is +10°C - +25°C.

The information of this data sheet is normative and based on laboratory tests and practical experience. Teknos guarantees that the product quality conforms to our quality system. Teknos accepts, however, no liability for the actual application work, as this is to a great extent dependent on the conditions during handling and application. Teknos accepts no liability for any damage resulting from misapplication of the product. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.
