

TECHNICAL DATA SHEET

1 16.12.2014

TEKNOSEAL 4006-00

Page 1 of 1 End grain sealer

TEKNOSEAL 4006 is an aqueous product for the protection of corner joints and end grain on wood / alu windows.

TECHNICAL DATA

Binder: Synthetic binder.

Volatile organic compound

(VOC): See Safety Data Sheet.

Colour range: Colourless

APPLICATION DETAILS

Pre-treatment: The wood must be clean and free from wood dust and contamination. The moisture content of

the wood should be approx. 13 % and should not exceed 15 %.

All softwood and non-durable hardwood for exterior use should be treated with a wood

preservative and either primed or treated with a topcoat.

Application: Is applied by caulk gun or plastic bottle with spray nozzle. Smooth with a brush or the like.

Application conditions: The product is delivered ready for use.

Optimum temperature for products and surroundings: 18-22 °C

Do not use at temperatures below 10 °C.

Optimum relative air humidity: Approx. 50 %

Drying times: Recoating dry: Approx. 1-2 hours

The drying times are approximate and may vary according to wood quality, temperatures,

humidity, ventilation and film thickness.

Cleaning: The equipment is cleaned with water.

HEALTH AND SAFETY See Safety Data Sheet.

ADDITIONAL INFORMATION

Pack size: 20 l

Storage: The product must be stored at temperatures above 10 °C. Shelf life in unopened containers: See

"Best before date" on the label. Keep containers tightly closed after use.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.