

TECHNICAL DATA SHEET

3 02.09.2014

TEKNOSTAIN 1974

1974-XX

TYPE Solvent based stain formulated of colour stable dyes and fast evaporating solvents.

USE For staining of all sorts of wood. Can be over-coated with all Teknos lacquers -

acid curing-, nitrocellulose, water borne- and UV lacquers.

The stain can be used for tinting of nitrocellulose and acid curing lacquers.

SPECIAL PROPERTIES TEKNOSTAIN 1974 provides a smooth and nice staining on all sorts of wood with

hardly no raising of wood fibres.

TECHNICAL DATA

Delivery viscosity 12-14 s DIN 4.

Specific gravity 0.82 kg/l

Total mass of solids Approx. 2-64 g/l dependent on the colour.

Volatile organic compound

(VOC)

See Safety Data Sheet.

Storage: See label.

Store in a tightly closed container.

Application method Spraying or brush.

Drying method Air and oven drying.

DIRECTIONS FOR USE

Drying Dry for handling after 15 minutes at 20 °C.

Dry for overcoating after 30 minutes at 20 °C.

Recommended amount to be

applied

Varying to the wanted covering of colour.

Cleaning TEKNOSOLV 1181.

HEALTH AND SAFETY See Safety Data Sheet.

ADDITIONAL INFORMATION Stir well before use.

A trial staining should be carried out to check the colour as variations of structure and natural colour of the wood and method of application may cause a considerable

colour deviation compared to the sample approved.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.