

TYPE	Water borne stain.
USE	All types of wood. Intended for indoor use.
SPECIAL PROPERTIES	TEKNOSTAIN AQUA 1996-00 is based on soluble dyestuff, pigments and binder.

TECHNICAL DATA

Density	Approx. 1.0 – 1.2 kg/l - depending of the colour shade.
Solids	Approx. 1 - 25 % by weight - depending of the colour shade.
Volatile organic compound (VOC)	See Safety Data Sheet
Spreading rate	8-10 m ² /l
Storage	See label

DIRECTIONS FOR USE

Application method	Spraying, dipping and flow coat.				
Drying time	<table><tr><td><u>20 °C</u></td><td><u>50 °C</u></td></tr><tr><td>1 h</td><td>10 min.</td></tr></table>	<u>20 °C</u>	<u>50 °C</u>	1 h	10 min.
<u>20 °C</u>	<u>50 °C</u>				
1 h	10 min.				
Thinner	Water				
Cleaning	Water or TEKNOCLEAN 1954-00, 1T021010.				

HEALTH AND SAFETY	See Safety Data Sheet
--------------------------	-----------------------

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.