
| | |
|---------------------------|---|
| TYPE | Water borne stain concentrate. |
| USE | For industrial treatment of all spruce and pine. Suitable for colouring of pallets. |
| SPECIAL PROPERTIES | TEKNOSTAIN AQUA 1996-11 is based on pigment and binder. |

TECHNICAL DATA

| | | |
|--|---|------------------------|
| Density | Approx. 1.03-1.10 kg/l – depending on the colour. | |
| Solids | Approx. 20-40 % - depending on the colour. | |
| Volatile organic compound (VOC) | See Safety Data Sheet. | |
| Drying time | <u>20 °C</u> 20 min. | <u>50 °C</u> 5 min. |
| Storage | See label. | |

DIRECTIONS FOR USE

| | | |
|---------------------------|--|----------|
| Application method | Spraying, dipping and flow coat. | |
| Thinner | Water | |
| Mixing ratio | TEKNOSTAIN AQUA 1996-11: | 1 part |
| | Water: | 10 parts |
| Cleaning | Water or TEKNOCLEAN 1954-00, 1T021010. | |

| | |
|--------------------------|------------------------|
| HEALTH AND SAFETY | See Safety Data Sheet. |
|--------------------------|------------------------|

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.
