

TIMANTTI 60 A

semigloss dispersion paint

PAINT TYPE	A semigloss, water-borne acrylate paint for interior use. Contains agents that prevent the growth of mildew.		
USAGE	Especially suited for use on demanding interior walls and ceilings in nuclear power plants. TIMANTTI 60 A can be applied onto, concrete, light-concrete, gypsum, plaster, stopper, brick and interior building board surfaces according to the painting directions. Also suitable for repainting old alkyd and dispersion paint coats.		
<hr/>			
TECHNICAL DATA			
Solids	About 38 % by volume		
Volatile organic compound (VOC)	EU VOC limit value (kat A/b): 100 g/l 2010. The product's VOC: max. 100 g/l.		
Practical spreading rate	Previously painted surface	7 - 10 m²/l	
	Stopper and wood fibre board	6 - 8 m²/l	
	Concrete and plastered surface	4 - 7 m²/l	
Density	abt. 1.3 g/ml		
Drying time +23°C, the relative air humidity 50%			
- dust free	after 2 hours		
- overcoatable	after 4 hours		
Thinner, clean up	Water. Wash the equipment immediately after use with detergent and warm water.		
Finish	Semigloss		
Colours	White. Can be tinted to shades of the white base paint according to the Interior Colour Card. Base Paint 3 (for dust binding)		
Washability and wear resistance	Mechanical wear resistance of the painted surface is very good. The painted surface can be washed repeatedly. Wet scrub resistance, class 1 according to EN 13300.		

DIRECTION FOR USE**Surface preparation**

Clean new surfaces from dust and dirt.
Wash previously painted surfaces with RENSA Paint Washing Liquid and rinse thoroughly with water.
Matt down hard or gloss surfaces by sanding and thereafter remove the dust.

Priming

IN DRY AREAS prime the surfaces previously mentioned with TIMANTTI 3 Primer.

Stopping, smoothing

Water-borne TEKNOFILL 5770 A light filler can be used for stopping and filling.

Application

Before use stir the paint thoroughly.
The paint is thinned with water when needed.
Reserve a sufficient amount of paint in the same vessel for each uniform surface. Colour differences will thus be avoided.
Apply by brush, roller or spray.

Application conditions

The surface to be painted must be dry.
During the application and drying period the temperature of the ambient air, the surface and the paint shall be above +5°C and the relative air humidity below 80%.
Good ventilation during the application and drying period quickens the drying process.

Storage

Must not freeze.

The information of this data sheet is based on laboratory tests and practical experience. The figures are for guidance only and depend on, for example, colour and gloss. As we have no control over the use and application conditions, we are only responsible for the quality of the product and guarantee that it conforms to our quality control. We accept no liability for any loss or damage resulting from the application of the product contrary to the directions or the intended use. The latest versions of our data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.
